

Amendment to the Claims:

This listing of claims will replace all prior versions, and listings of claims in the application:

Listing of Claims:

Claim 1-9 (Cancelled).

⁵
Claim ~~10~~. (Previously Presented): The method of Claim 21 wherein C is a diepoxide.

Claim 11. (Cancelled).

⁰ Claim ~~12~~. (Previously Presented): The method of Claim ⁴~~22~~ wherein C is a diepoxide.

⁷
Claim ~~13~~. (Previously Presented): A molded article obtained by the method of Claim ~~10~~.

⁸
² Claim ~~14~~. (Previously Presented): A molded article obtained by the method of Claim ~~20~~.

⁹
³ Claim ~~15~~. (Previously Presented): A molded article obtained by the method of Claim ~~21~~.

¹⁰
⁴ Claim ~~16~~. (Previously Presented): A molded article obtained by the method of Claim ~~22~~.

Claim 17-18 (Cancelled).

¹
Claim ~~19~~. (Currently Amended): A method of using a reinforced molding compositions wherein the resin is at least one member selected from the group consisting of (co)polyamide 6 and (co)polyamide 66, (co)polyamide 6,6 the Mo-7058

composition characterized in that its viscosity at a shear velocity of 10 s^{-1} is greater than $1000 \text{ s}^{-4} \text{ Pas}$, and at a shear velocity of 1000 s^{-1} its viscosity is less than 300 Pas at a processing temperature that is 40 to 80°C above the melting point of the molding composition, said method comprising preparing an article by thermoforming.

²
Claim 20. (Previously Presented): The method of Claim ¹~~19~~ wherein the viscosity is greater than 1500 Pas at shear velocity of 10 s^{-1} and is less than 280 Pas at shear velocity of 1000 s^{-1} .

³
Claim ~~21~~. (Previously Presented): The method of Claim ¹~~19~~ wherein the composition comprise A) 98 to 41 parts by weight of said resin and B) 2 to 50 parts by weight of reinforcing materials, and C) 0.1 to 4 parts by weight of branching additives and/or additives raising the molecular weight and D) 0 to 5 parts by weight of further additives, the sum of the parts by weight of A, B, C, D totaling 100.

⁴
Claim ~~22~~. (Previously Presented): The method of Claim ¹~~19~~ wherein the composition comprise A) 67 to 85 parts by weight of said resin and B) 15 to 30 parts by weight of reinforcing materials, and C) 0.2 to 1 part by weight of branching additives and/or additives raising the molecular weight, D) 0.1 to 2 parts by weight of further additives, the sum of the parts by weight of A, B, C and D totaling 100.